



PRODUCT DATA SHEET

Krystalkrete

DESCRIPTION

Krystalkrete®, Exposed Aggregate Pool finishes are blends of enriched White Portland cement and special Quartz aggregates. Krystalkrete® offers the pool builder an alternative to conventional pool finishes by using combinations of different quartz sizes and colors, as well as, a variety of pigments. Krystalkrete® is available in many attractive colors which allows the pool builder and homeowner limitless flexibility in tile and accessory selection. Although application and finishing techniques are not difficult to learn, Krystalkrete® is intended for use by professional applicators.

BENEFITS

Proven Durability • Extremely Etch Resistant • High Compressive Strength • AquaGem Color Quartz • Traditionally or Spray Applied • Easy Maintenance

PREPARATION

Krystalkrete® should be applied to a sound surface free of oil, dirt, algae or any other foreign substance. Previously applied paints or sealers must be removed by acid washing and/or sandblasting. Neutralize acid with baking soda or soda ash then thoroughly rinse with water. In addition to, or in partial replacement of the procedures mentioned above, PERMAKOTE™ can be used as a bonding coat. Re-finished pools must be undercut an appropriate distance around all tile, return lines, light fixtures and main drains [follow APSP and/or NPC standards]. All weepers and plumbing leaks should be repaired at least 24 hours prior to plaster application. Always follow "sound technical practices" as recommended by The National Plasters (NCP), The Association of Pool and Spa Professionals (APSP), and The American Concrete Institute (ACI).

MIXING

1. Using standard mixing equipment, it is important to blend each batch with the same amount of water and to mix each batch for the same amount of time.
2. Mix Krystalkrete® with approximately 1½ to 1¾ gallons of potable water per 80 lb. bag.
3. Start the mixing procedure by adding approximately two thirds of the total water requirements to the mixer, add Krystalkrete® then the balance of water.
4. Mix the completed batch for at least 8 minutes to ensure a proper blend of all ingredients.
5. Before using any jobsite additives, please consult your C.L. Industries Product Service Representative.

CURING

Care should be taken to protect Krystalkrete® from rapid drying conditions such as high wind, high temperature, low humidity. Such precautions may include fogging or misting the surface, or placing a protective covering over the pool. Cover should not be placed on the plaster surface.

FILLING PROCEDURES

When filling a pool it is important to do so without interruption of fill water. Fill pool as rapidly as possible. All fill hoses should have a sock or cloth on the end. Do not allow main hose length to lay on the aggregate surface as it will leave a mark.

WATER CHEMISTRY

Water chemistry should be maintained within +/- 0.3 on the Langelier Saturation Index. Chlorine should not exceed 3 PPM and Cyanuric acid levels should not exceed manufacturers' 40 to 60 PPM recommendations. For more information on chemical balance and the Saturation Index see recommendations from the NPC, National Plasterers' Council, www.npconline.org and APSP, Association of Pool & Spa Professionals, www.theapsp.org. Failure to monitor and maintain proper chemical balance will result in equipment damage as well as surface deterioration. Maintaining proper chemical balance is essential during the initial curing phase as well as routine maintenance to maximize the life of the pool surface.

COVERAGE

Each 80 lb. bag covers approximately 18–22 sq. feet. The surface condition will have a direct relationship on the thickness of application and the corresponding coverage rate per bag.

PACKAGING

Krystalkrete® is packaged in 80 lb. heavy duty 3-ply paper bags with polyethylene moisture barrier linings.

WARNING

Product is alkaline on contact with water. During mixing or application, avoid contact with eyes or skin. In case of such contrast, flood eyes repeatedly with water and call physician. Do not take internally. Wear NIOSH approved mask during mixing procedures.

C.L. Industries
PO Box 490180 • Leesburg, FL 34749-0180
407/608-5481 • 800/333.2660 • www.clindustries.com